

TABLE 4

MECHANICAL PROPERTIES OF IMPACT-MODIFIED

POLYOLEFIN COPOLYMER

	NEAT POLYMER	1.0WT% A1-325 POLYMER
Notched Izod Impact		
@ 73°F (ft-lb/in)	2.0	2.4
@ -4°F (ft-lb/in)	1.0	1.1
Heat Deflection Temperature		
°C @ 66 psi	99	105
Gardner Impact		
@ -4°F (in-lbs)	100	140